



杭州千岛湖阿尔派进出口贸易有限公司
HANGZHOU QIANDAO LAKE ALPINE FOREIGN TRADE LTD.

NO. 11 BUILDING 42 JINGHU GARDEN QIANDAO LAKE TOWN CHUN' AN COUNTY,

HANGZHOU, ZHEJIANG, CHINA

DTY		
Lot No.		
Yarn Counts		165D/288F/6 SIM
Color		BLUE
Liner density	dtex	1237.19
Deviation of Liner	%	3.57
Breaking Strength	Cn/dtex	3.22
Breaking Elongation	%	18.64
Boiling Shrinkage	%	2.33
Oil content	%	1.74
Winding Stability	%	81.04
Intermingled Nips	N/ M	35

DTY		
Lot No.		
Yarn Counts		150D/288F/2 LIM
Color		RAW WHITE
Liner density	dtex	368.21
Deviation of Liner	%	3.85
Breaking Strength	Cn/dtex	3.37
Breaking Elongation	%	18.54
Boiling Shrinkage	%	2.46
Oil content	%	1.78
Winding Stability	%	79.36
Intermingled Nips	N/ M	25



杭州千岛湖阿尔派进出口贸易有限公司
HANGZHOU QIANDAO LAKE ALPINE FOREIGN TRADE LTD.

NO. 11 BUILDING 42 JINGHU GARDEN QIANDAO LAKE TOWN CHUN' AN COUNTY,
HANGZHOU, ZHEJIANG, CHINA

DTY		
Lot No.		
Yarn Counts		150D/192F/2 LIM
Color		PURPLE
Liner density	dtex	366.37
Deviation of Liner	%	3.69
Breaking Strength	Cn/dtex	3.29
Breaking Elongation	%	19.13
Boiling Shrinkage	%	2.92
Oil content	%	1.82
Winding Stability	%	80.54
Intermingled Nips	N/ M	25

DTY		
Lot No.		
Yarn Counts		150D/48F/2 HIM
Color		RED
Liner density	dtex	327.49
Deviation of Liner	%	2.87
Breaking Strength	Cn/dtex	3.17
Breaking Elongation	%	20.33
Boiling Shrinkage	%	2.74
Oil content	%	2.66
Winding Shrinkage	%	13.52
Winding Stability	%	78
Intermingled Nips	N/M	100



杭州千岛湖阿尔派进出口贸易有限公司
HANGZHOU QIANDAO LAKE ALPINE FOREIGN TRADE LTD.

NO. 11 BUILDING 42 JINGHU GARDEN QIANDAO LAKE TOWN CHUN' AN COUNTY,

HANGZHOU, ZHEJIANG, CHINA

DTY		
Lot number		/
Yarn Counts		150D/48F NIM
Color		BLACK
Liner density	dtex	167.43
Deviation of Liner	%	3.54
Breaking Strength	Cn/dtex	3.24
Breaking Elongation	%	22.36
Boiling Shrinkage	%	3.48
Oil content	%	2.29
Winding Shrinkage	%	12.72
Winding Stability	%	69
Intermingled Nips	N/M	0

DTY		
Lot number		/
Yarn Counts		50D/36F NIM
Color		BLEACH WHITE
Liner density	dtex	56
Deviation of Liner	%	3.24
Breaking Strength	Cn/dtex	3.31
Breaking Elongation	%	22.04
Boiling Shrinkage	%	2.64
Oil content	%	2.5
Winding Shrinkage	%	19.15
Winding Stability	%	81.15
Intermingled Nips	N/M	0



杭州千岛湖阿尔派进出口贸易有限公司
HANGZHOU QIANDAO LAKE ALPINE FOREIGN TRADE LTD.

NO. 11 BUILDING 42 JINGHU GARDEN QIANDAO LAKE TOWN CHUN' AN COUNTY,

HANGZHOU, ZHEJIANG, CHINA

DTY		
Lot No.		
Yarn Counts		75D/36F NIM
Color		GREEN
Liner density	dtex	82.75
Deviation of Liner	%	2.34
Breaking Strength	Cn/dtex	3.35
Breaking Elongation	%	24.36
Boiling Shrinkage	%	2.34
Oil content	%	2.58
Winding Shrinkage	%	17.27
Winding Stability	%	74
Intermingled Nips	N/M	/

FDY		
Lot No.		
Yarn Counts		150D/48F TBR
Color		GOLDEN
Liner density	dtex	168
Deviation of Liner	%	0.5
Breaking Strength	Cn/dtex	4.21
Breaking Elongation	%	32.21
Boiling Shrinkage	%	7
Oil content	%	0.97